

## Park Electrochemical Nelcote® F-554 Phenolic Prepreg, Chopped Molding Compound Reinforced

Category : Polymer , Thermoset , Phenolic

### Material Notes:

Nelcote® F-554 is a high purity silica filled phenolic resin coated on Commercial or Aerospace grade silica fabric. F-554 is used in the manufacture of intermediate temperature ablative rocket nozzles, heat shields, and combustion chambers in highly oxidative environments. Key Features and Benefits: Provides a combination of high-strength and ablative properties for demanding applications. Low thermal expansion. Good Tack and Drape properties. Conforms to MIL-R-9299. Applications/Qualifications: Rocket Nozzles, Combustion Chambers, Heat Shields, Rocket Motor Throat Sections. Information provided by Park Electrochemical Corp.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Park-Electrochemical-Nelcote-F-554-Phenolic-Prepreg-Chopped-Molding-Compound-Reinforced.php](http://www.lookpolymers.com/polymer_Park-Electrochemical-Nelcote-F-554-Phenolic-Prepreg-Chopped-Molding-Compound-Reinforced.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.70 g/cc	1.70 g/cc	ASTM D792
Volatiles	2.0 - 4.0 % @Temperature 163 °C	2.0 - 4.0 % @Temperature 325 °F	10 min

Mechanical Properties	Metric	English	Comments
Hardness, Barcol	75	75	ASTM D2583
Tensile Strength, Yield	62.1 MPa @Temperature 23.9 °C	9000 psi @Temperature 75.0 °F	0° Direction, Dry; 325°F 2kpsi; ASTM D638
Tensile Modulus	26.2 GPa @Temperature 23.9 °C	3800 ksi @Temperature 75.0 °F	0° Direction, Dry; 325°F 2kpsi; ASTM D638
Flexural Strength	110 MPa @Temperature 23.9 °C	16000 psi @Temperature 75.0 °F	Dry; 325°F 2kpsi; ASTM D790
Flexural Modulus	20.7 GPa @Temperature 23.9 °C	3000 ksi @Temperature 75.0 °F	Dry; 325°F 2kpsi; ASTM D790
Compressive Strength	276 MPa @Temperature 23.9 °C	40000 psi @Temperature 75.0 °F	Dry; 325°F 2kpsi; ASTM D695
Compressive Modulus	13.8 GPa @Temperature 23.9 °C	2000 ksi @Temperature 75.0 °F	Dry; 325°F 2kpsi; ASTM D695

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Specific Heat Capacity Thermal Properties	0.962 J/g-°C Metric	0.230 BTU/lb-°F English	ASTM C351 Comments
Thermal Conductivity	3.89 W/m-K @Temperature 149 °C	27.0 BTU-in/hr-ft <sup>2</sup> -°F @Temperature 300 °F	ASTM C177

Processing Properties	Metric	English	Comments
Shelf Life	6.00 Month @Temperature 4.44 °C	6.00 Month @Temperature 40.0 °F	

Descriptive Properties	Value	Comments
Filler Content (%)	2-4	
Nominal Prepreg Weight (oz/yd)	30	
Resin Flow (%)	7-17	325°F, 150psi
Resin Solids Content (%)	30-36	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China