

Parker Chomerics CHO-SEAL E6434 Conductive Elastomer

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Conductive Elastomer EMI/EMP Gaskets Information provided by Chomerics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Parker-Chomerics-CHO-SEAL-E6434-Conductive-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	3.65 - 4.15 g/cc	3.65 - 4.15 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	68 - 82	68 - 82	
Tensile Strength at Break	>= 1.38 MPa	>= 200 psi	ASTM D412
Elongation at Break	>= 200 %	>= 200 %	ASTM D412
Tear Strength	13.125 kN/m	74.891 pli	
Compression Set	40 %	40 %	70 hrs @ 100°C; ASTM D395 Method B

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	125 °C	257 °F	
Minimum Service Temperature, Air	-45.0 °C	-49.0 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	0.0060 ohm-cm	0.0060 ohm-cm	as supplied without pressure sensitive adhesive
Shielding Effectiveness	>= 85 dB	>= 85 dB	2 GHz (Plane Wave); MIL-G-83528
	>= 85 dB	>= 85 dB	10 GHz (Plane Wave); MIL-G-83528
	>= 100 dB	>= 100 dB	500 MHz (E Field); MIL-G-83528
	>= 105 dB	>= 105 dB	100 MHz (E Field); MIL-G-83528

Descriptive Properties	Value	Comments
Binder	EPDM	
Filler	Ag/Ni	
Heat Aging ohm-cm max	0.0125	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China