

Parker Chomerics Frame Gasketing Wire Mesh EMI Gasket Selection Guide

Category : Metal

Material Notes:

Construction: Formed Knitted Wire Strips Clamped in Aluminum Extrusions Available Forms: Strips, Fab. Lengths, Frames with Joined EMI Strips..Standard Metals Available in EMI Portion: Monel Ferrex Information provided by Chomerics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Parker-Chomerics-Frame-Gasketing-Wire-Mesh-EMI-Gasket-Selection-Guide.php

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	66.0 °C	151 °F	Neoprene Version
	204 °C	399 °F	Silicone Version
Minimum Service Temperature, Air	-62.0 °C	-79.6 °F	Silicone Version
	-34.0 °C	-29.2 °F	Neoprene Version

Electrical Properties	Metric	English	Comments
Shielding Effectiveness	20 - 30 dB	20 - 30 dB	
	@Frequency 14000 Hz	@Frequency 14000 Hz	
	>= 93 dB	>= 93 dB	
	@Frequency 1.00e+9 Hz	@Frequency 1.00e+9 Hz	
	>= 102 dB	>= 102 dB	
	@Frequency 1.80e+7 Hz	@Frequency 1.80e+7 Hz	

Descriptive Properties	Value	Comments
Maximum Joint Unevenness, % of Gasket Height	0.25	Class B- Open-Close in Same Position
	0.25	Class C- Completely Interchangeable
	0.3	Class A- Permanently Closed

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China