

Parker Chomerics Tecknit SC-Consil® 860 Carbon-Filled Silicone Elastomer

Category : Polymer , Thermoset , Silicone

Material Notes:

Description: SC-CONSIL is a silicone elastomer filled with carbon particles. It provides superior shielding and a reliable environmental seal.

The combination of carbon particles and silicone allows SC-CONSIL to maintain its physical and electrical properties over an extremely wide temperature range. SC-CONSIL is manufactured in sheets, molded and continuously extruded strips, and in die-cut gasket

Typical Applications SC-CONSIL provides excellent voltage handling capabilities for grounding, lower current densities, and is ideal for static discharge and corona applications. Various extruded shapes designed for groove and flange mounting, such as tubes and P-shapes, provide maximum deflection at low to medium closure pressures. SC-CONSIL also provides a good environmental seal under moderate closing forces

Information provided by Chomerics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Parker-Chomerics-Tecknit-SC-Consil-860-Carbon-Filled-Silicone-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 - 1.31 g/cc	1.25 - 1.31 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65 - 75	65 - 75	ASTM D2240
Tensile Strength	>= 3.45 MPa	>= 500 psi	ASTM D412
Elongation at Break	>= 75 %	>= 75 %	ASTM D412
Tear Strength	8.77 kN/m	50.0 pli	ASTM D624

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	177 °C	351 °F	
Minimum Service Temperature, Air	-51.0 °C	-59.8 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	<= 3.0 ohm-cm	<= 3.0 ohm-cm	
Shielding Effectiveness	68 dB	68 dB	Plane Wave
	@Frequency 1.00e+9 Hz	@Frequency 1.00e+9 Hz	
	77 dB	77 dB	E-Field
	@Frequency 1.00e+7 Hz	@Frequency 1.00e+7 Hz	
	88 dB	88 dB	

Electrical Properties	Metric	English	Plane Wave Comments
	@Frequency 1.00e+10 Hz	@Frequency 1.00e+10 Hz	
	93 dB	93 dB	H-Field
	@Frequency 100000 Hz	@Frequency 100000 Hz	

Descriptive Properties	Value	Comments
Binder	Silicone	
Color	Black	
Filler	Carbon	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China