

Phillips 66 COPYLENE® CH043L Polypropylene, Homopolymer, Lube, Straw

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Extrusion Grade

Material Notes:

COPYLENE™ CH043L is a high antistatic, medium flow polypropylene homopolymer resin, suitable for injection molding or extrusion applications. Applications: Housewares. Equivalent to Pro-fax® HL782K Information provided by Phillips 66.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Phillips-66-COPYLENE-CH043L-Polypropylene-Homopolymer-Lube-Straw.php

Physical Properties	Metric	English	Comments
Density	0.902 g/cc	0.0326 lb/in ³	ASTM D792
Melt Flow	4.3 g/10 min @Load 2.16 kg, Temperature 230 °C	4.3 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	90	90	ASTM D785
Tensile Strength, Yield	35.9 MPa	5200 psi	2 in/min; ASTM D638
Elongation at Yield	9.0 %	9.0 %	ASTM D638
Flexural Modulus	1.52 GPa	220 ksi	0.05 in/min; 1% secant; Procedure A; ASTM D790
Izod Impact, Notched	0.267 J/cm @Temperature 23.0 °C	0.500 ft-lb/in @Temperature 73.4 °F	Method A; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	99.0 °C	210 °F	unannealed; ASTM D648

Descriptive Properties	Value	Comments
Process	Extrusion	
	Injection Molding	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China