

## Plaskolite Optix® CA-71 General Purpose Acrylic Resin

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, General Purpose, Molded

### Material Notes:

Injection Molding and Extrusion Grade Pellets. High heat resistance, medium flow.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Plaskolite-Optix-CA-71-General-Purpose-Acrylic-Resin.php](http://www.lookpolymers.com/polymer_Plaskolite-Optix-CA-71-General-Purpose-Acrylic-Resin.php)

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in <sup>3</sup>	ASTM D792
Melt Flow	4.3 g/10 min	4.3 g/10 min	Condition 230/2-8; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	68.0 MPa	9860 psi	ASTM D638
Elongation at Break	5 %	5 %	ASTM D638
Modulus of Elasticity	3.20 GPa	464 ksi	ASTM D638
Flexural Strength	105 MPa	15200 psi	ASTM D790
Izod Impact, Notched	0.160 J/cm	0.300 ft-lb/in	ASTM D256
Gardner Impact	0.226 J	0.167 ft-lb	Falling Weight; ASTM D3029GB

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	97.0 °C	207 °F	ASTM D648
Vicat Softening Point	107 °C	225 °F	ASTM D1525
Flammability, UL94	HB	HB	

Optical Properties	Metric	English	Comments
Transmission, Visible	92 %	92 %	Luminous Transmittance, ASTM D1003

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China