

Plaskolite Optix® CA-75 General Purpose Acrylic Resin

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, General Purpose, Molded

Material Notes:

Injection Molding and Extrusion Grade Pellets. Highest heat resistance, medium flow.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plaskolite-Optix-CA-75-General-Purpose-Acrylic-Resin.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ASTM D792
Melt Flow	3.6 g/10 min	3.6 g/10 min	Condition 230/2-8; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	71.0 MPa	10300 psi	ASTM D638
Elongation at Break	4.2 %	4.2 %	ASTM D638
Modulus of Elasticity	2.30 GPa	334 ksi	ASTM D638
Flexural Strength	121 MPa	17500 psi	ASTM D790
Izod Impact, Notched	0.160 J/cm	0.300 ft-lb/in	ASTM D256
Gardner Impact	0.226 J	0.167 ft-lb	Falling Weight; ASTM D3029GB

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	90.0 °C	194 °F	UL 746 ABC
Deflection Temperature at 1.8 MPa (264 psi)	100 °C	212 °F	ASTM D648
Vicat Softening Point	113 °C	235 °F	ASTM D1525
Flammability, UL94	HB	HB	

Optical Properties	Metric	English	Comments
Transmission, Visible	92 %	92 %	Luminous Transmittance, ASTM D1003

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China