

## Plaslok 308 Black (INJ) Mineral/Flock Filled Phenolic Molding Compound (discontinued \*\*)

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Phenolic , Phenolic, Novolac, Mineral/Flock Filled

### Material Notes:

Plaslok Corporation was purchased by Plastics Engineering Company (maker of Plenco brand materials) in March 2000. The Plaslok name is no longer in use. Plaslok 308 is a two-stage, mineral and flock-filled phenolic molding compound designed to withstand the hostile environment of high abrasion and high tangential speed of engine pulleys. It is characterized by both exceptional strength and good surface appearance. Data provided by Plaslok Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Plaslok-308-Black-INJ-MineralFlock-Filled-Phenolic-Molding-Compound-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Plaslok-308-Black-INJ-MineralFlock-Filled-Phenolic-Molding-Compound-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.46 g/cc	0.0527 lb/in <sup>3</sup>	ASTM D792
Apparent Bulk Density	0.500 g/cc	0.0181 lb/in <sup>3</sup>	ASTM D1895
Water Absorption	0.40 %	0.40 %	ASTM D570
Linear Mold Shrinkage	0.0090 cm/cm	0.0090 in/in	Injection; ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	56.0 MPa	8120 psi	ASTM D638
Flexural Yield Strength	86.0 MPa	12500 psi	ASTM D790
Flexural Modulus	6.90 GPa	1000 ksi	ASTM D790
Compressive Yield Strength	235 MPa	34100 psi	ASTM D695
Izod Impact, Notched	0.210 J/cm	0.393 ft-lb/in	ASTM D256

Electrical Properties	Metric	English	Comments
Electrical Resistivity	2.20e+10 ohm-cm	2.20e+10 ohm-cm	ASTM D257
Dielectric Strength	12.2 kV/mm	310 kV/in	ASTM D149
Comparative Tracking Index	180 V	180 V	UL 746

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China