

## Plastcom SLOVALEN PQ 81 T 15 PP, 15% mineral filling

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Talc Filler , Polypropylene with 20% Talc Filler

### Material Notes:

Features Modified PP for injection moulding with the content of 15% mineral filling. Increased rigidity, strength and thermal use up to 130°C depending on the talc content. Decreased shrinkage. General application in all industry branches - packing material, garden flower-pots, toys, furniture industry, dowels, clamps, hinge, office chairs, hangers, covers of car chassis, fenders, motors etc. Packaging, transport, stocking The product is packed in hermetically closed thick-walled 25 kg PE bags, on a 1.000 kg palette coated in a stretch foil, in big bags with a thick PE foil fixed on a 1.000 kg palette, in paper octabins with a thick PE foil fixed on a 1.000 kg palette or in other packaging according to customer requirements. The transport is provided in closed-up vehicles where the material is protected against movement and mechanical damage. The product requires stocking in closed-up, dry places protected against sun and thermal radiation. Information Provided by Plastcom spol. s r.o.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Plastcom-SLOVALEN-PQ-81-T-15-PP-15-mineral-filling.php](http://www.lookpolymers.com/polymer_Plastcom-SLOVALEN-PQ-81-T-15-PP-15-mineral-filling.php)

Physical Properties	Metric	English	Comments
Density	1.03 g/cc	0.0372 lb/in <sup>3</sup>	
Linear Mold Shrinkage	0.011 cm/cm	0.011 in/in	
Linear Mold Shrinkage, Transverse	0.011 cm/cm	0.011 in/in	
Melt Flow	8.0 g/10 min @Load 0.325 kg, Temperature 270 °C	8.0 g/10 min @Load 0.716 lb, Temperature 518 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	15.0 MPa	2180 psi	
Elongation at Break	6.0 %	6.0 %	
Tensile Modulus	1.10 GPa	160 ksi	
Flexural Strength	17.0 MPa	2470 psi	
Flexural Modulus	1.02 GPa	148 ksi	
Charpy Impact Unnotched	NB	NB	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	NB	NB	
	@Temperature -20.0 °C	@Temperature -4.00 °F	
Charpy Impact, Notched	4.80 J/cm <sup>2</sup>	22.8 ft-lb/in <sup>2</sup>	
	@Temperature -20.0 °C	@Temperature -4.00 °F	

Mechanical Properties	Metric	English	Comments
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	65.0 °C	149 °F	
Vicat Softening Point	115 °C	239 °F	B

Processing Properties	Metric	English	Comments
Melt Temperature	200 - 250 °C	392 - 482 °F	
Mold Temperature	40.0 - 50.0 °C	104 - 122 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	4 hour	4 hour	
Injection Pressure	70.0 - 120 MPa	10200 - 17400 psi	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China