

## PlastiComp Complet® LGF50 - PA66 MT Nylon 66, 50% Long Glass Fiber Reinforced, Impact Modified

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 50% Glass Fiber Filled , Nylon 66, Glass Reinforced, Impact Grade

### Material Notes:

Complet® long-fiber reinforced pellets are manufactured to exceed expectation for quality and performance. Nylon 6 with 50% long glass fiber reinforcement. Impact modified. Information provided by PlastiComp, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PlastiComp-Complet-LGF50-PA66-MT-Nylon-66-50-Long-Glass-Fiber-Reinforced-Impact-Modified.php](http://www.lookpolymers.com/polymer_PlastiComp-Complet-LGF50-PA66-MT-Nylon-66-50-Long-Glass-Fiber-Reinforced-Impact-Modified.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.60 g/cc	1.60 g/cc	ASTM D-792
Filler Content	50 %	50 %	Long Glass Fiber

Mechanical Properties	Metric	English	Comments
Tensile Strength	221 MPa	32100 psi	ASTM D-638
Elongation at Break	2.0 - 3.0 %	2.0 - 3.0 %	ASTM D-638
Tensile Modulus	15.172 GPa	2200.5 ksi	ASTM D-638
Flexural Strength	360 MPa	52200 psi	ASTM D-790
Flexural Modulus	11.724 GPa	1700.4 ksi	ASTM D-790
Izod Impact, Notched	6.51 J/cm	12.2 ft-lb/in	ASTM D-256
Izod Impact, Unnotched	18.16 J/cm	34.02 ft-lb/in	ASTM D-4812

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	246 °C	475 °F	ASTM D-648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	282 - 299 °C	540 - 570 °F	
Middle Barrel Temperature	288 - 304 °C	550 - 580 °F	
Front Barrel Temperature	293 - 310 °C	560 - 590 °F	
Nozzle Temperature	288 - 304 °C	550 - 580 °F	
Melt Temperature	293 - 310 °C	560 - 590 °F	

Mold Temperature Processing Properties	93.3 °C Metric	200 °F English	Comments
Injection Velocity	50.8 - 76.2 mm/sec	2.00 - 3.00 in/sec	
Drying Temperature	85.0 °C @Time 14400 sec	185 °F @Time 4.00 hour	
Moisture Content	<= 0.18 %	<= 0.18 %	
Back Pressure	0.172 - 0.345 MPa	25.0 - 50.0 psi	
Cushion	0.635 cm	0.250 in	
Screw Speed	30 - 50 rpm	30 - 50 rpm	

Descriptive Properties	Value	Comments
Injection Pressure	Medium to maximum	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China