

Plastics Group Polifil® GFRMPPCC-30 30% Glass Reinforced Polypropylene, High Impact

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Glass Fiber Filler

Material Notes:

Polifil® GFRMPPCC series compounds are high impact polypropylenes reinforced with chemically coupled glass fibers. This combination provides higher impact strength while retaining high stiffness. Applications: Appliances Electrical components Automotive Utility products
Standard processing techniques are applicable. Information provided by The Plastics Group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plastics-Group-Polifil-GFRMPPCC-30-30-Glass-Reinforced-Polypropylene-High-Impact.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ASTM D792
Filler Content	30 %	30 %	ASTM D2584
Linear Mold Shrinkage	0.0035 cm/cm @Thickness 1.59 mm	0.0035 in/in @Thickness 0.0625 in	ASTM D955
Melt Flow	5.0 - 10 g/10 min	5.0 - 10 g/10 min	230/2.16; May be specified; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	68.9 MPa	10000 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	83.4 MPa	12100 psi	ASTM D638
Flexural Modulus	3.86 GPa	560 ksi	Tangent; ASTM D790
Izod Impact, Notched	1.60 J/cm	3.00 ft-lb/in	At 73°F; ASTM D256
Gardner Impact	0.904 J	0.667 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	149 °C	300 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	132 °C	270 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China