

## Plastics Group Polifil® RMT-30 30% Talc-Reinforced Polypropylene, High Impact

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Talc Filler

### Material Notes:

Polifil® RMT series compounds are high impact polypropylenes reinforced with asbestos-free talc. In addition to high impact strength, they possess a high flex modulus and high heat deflection resistance. These compounds are used in automotive applications and conform to the requirements of the FMVSS-302. Standard processing techniques are applicable. Information provided by The Plastics Group.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Plastics-Group-Polifil-RMT-30-30-Talc-Reinforced-Polypropylene-High-Impact.php](http://www.lookpolymers.com/polymer_Plastics-Group-Polifil-RMT-30-30-Talc-Reinforced-Polypropylene-High-Impact.php)

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in <sup>3</sup>	ASTM D792
Filler Content	30 %	30 %	ASTM D2584
Linear Mold Shrinkage	0.011 cm/cm @Thickness 1.59 mm	0.011 in/in @Thickness 0.0625 in	ASTM D955
Melt Flow	8.0 - 12 g/10 min	8.0 - 12 g/10 min	230/2.16; May be specified; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	87	87	ASTM D785
Tensile Strength at Break	26.72 MPa	3875 psi	ASTM D638
Flexural Modulus	2.52 GPa	365 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.721 J/cm	1.35 ft-lb/in	At 73°F; ASTM D256
Izod Impact, Unnotched	4.91 J/cm	9.20 ft-lb/in	At 73°F; ASTM D256
Gardner Impact	4.858 J	3.583 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	122 °C	252 °F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China