

PlastxWorld CEVIAN® A1700 PA/ABS Alloy, DAM

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS)/Nylon Blend , Nylon

Material Notes:

Property data is for dry as molded (DAM) samples. Information provided by PlastxWorld Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PlastxWorld-CEVIAN-A1700-PAABS-Alloy-DAM.php

Physical Properties	Metric	English	Comments
Density	1.09 g/cc	0.0394 lb/in ³	ASTM D792
Water Absorption	0.98 %	0.98 %	24 hr; ASTM D570
Linear Mold Shrinkage	0.0090 cm/cm	0.0090 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	116	116	ASTM D785
Tensile Strength, Yield	46.9 MPa	6800 psi	ASTM 638
Elongation at Break	100 %	100 %	ASTM D635
Flexural Yield Strength	75.2 MPa	10900 psi	ASTM D790
Flexural Modulus	2.16 GPa	313 ksi	ASTM D790
Izod Impact, Notched	1.55 J/cm @Thickness 3.17 mm	2.90 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	105 °C	221 °F	0.25 inch; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	105 °C	221 °F	0.25 inch; ASTM D648
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China