

## PlastxWorld CEVIAN® B5524 20% GF PBT/ABS Alloy

Category : Polymer , Thermoplastic , ABS Polymer , ABS/Polyester Alloy + GF , Polyester, TP , Polybutylene Terephthalate (PBT)

**Material Notes:**

Glass fiber reinforced and flame retarded PBT/ABS alloy. Information provided by PlastxWorld Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PlastxWorld-CEVIAN-B5524-20-GF-PBTABS-Alloy.php](http://www.lookpolymers.com/polymer_PlastxWorld-CEVIAN-B5524-20-GF-PBTABS-Alloy.php)

Physical Properties	Metric	English	Comments
Density	1.42 g/cc	0.0513 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0025 - 0.0045 cm/cm	0.0025 - 0.0045 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	95.8 MPa	13900 psi	ASTM 638
Elongation at Break	2.4 %	2.4 %	ASTM D638
Flexural Yield Strength	132 MPa	19200 psi	ASTM D790
Flexural Modulus	6.47 GPa	939 ksi	ASTM D790
Izod Impact, Notched	0.694 J/cm @Thickness 3.17 mm	1.30 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	200 °C	392 °F	0.25 inch; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	125 °C	257 °F	0.25 inch; ASTM D648
UL RTI, Electrical	140 °C	284 °F	UL746B
UL RTI, Mechanical with Impact	95.0 °C	203 °F	UL746B
UL RTI, Mechanical without Impact	130 °C	266 °F	UL746B
Flammability, UL94	V-0 @Thickness 1.50 mm	V-0 @Thickness 0.0591 in	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China