

PlastxWorld CEVIAN®-N GRSJ3 30% GF SAN resin

Category : Polymer , Thermoplastic , SAN Polymer , Styrene Acrylonitrile (SAN), Molded, Glass Reinforced

Material Notes:

Glass fiber reinforced SAN resin. These are typical values and are not intended for specification purposes. UL approved file No. is E47773.

Information provided by PlastxWorld Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PlastxWorld-CEVIAN-N-GRSJ3-30-GF-SAN-resin.php

Physical Properties	Metric	English	Comments
Density	1.30 g/cc	0.0470 lb/in ³	ASTM D792
Water Absorption	0.30 %	0.30 %	24 hr; ASTM D570
Linear Mold Shrinkage	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	117 MPa	17000 psi	ASTM D638
Flexural Yield Strength	147 MPa	21300 psi	ASTM D790
Flexural Modulus	8.811 GPa	1278 ksi	ASTM D790
Izod Impact, Notched	0.481 J/cm @Thickness 3.17 mm	0.900 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	21.6 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$ @Temperature 20.0 $^\circ\text{C}$	12.0 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$ @Temperature 68.0 $^\circ\text{F}$	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	114 $^\circ\text{C}$	237 $^\circ\text{F}$	0.5 inch; ASTM D648
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China