

PlastxWorld CEVIAN® SER23 ABS

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Unreinforced, Flame Retardant

Material Notes:

General purpose and flame retarded ABS with excellent moldability and no plate-out. These are typical values and are not intended for specification purposes. UL approved file No. is E47773. Information provided by PlastxWorld Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PlastxWorld-CEVIAN-SER23-ABS.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ASTM D792
Water Absorption	0.30 %	0.30 %	24 hr; ASTM D570
Linear Mold Shrinkage	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D955
Melt Flow	13 g/10 min @Load 3.80 kg, Temperature 230 °C	13 g/10 min @Load 8.38 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength, Yield	37.9 MPa	5500 psi	ASTM 638
Flexural Yield Strength	73.8 MPa	10700 psi	ASTM D790
Flexural Modulus	2.10 GPa	305 ksi	ASTM D790
Izod Impact, Notched	2.03 J/cm @Thickness 3.17 mm	3.80 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	86.4 µm/m-°C @Temperature 20.0 °C	48.0 µin/in-°F @Temperature 68.0 °F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	82.0 °C	180 °F	0.5 inch; ASTM D648
Vicat Softening Point	90.0 °C	194 °F	ASTM D1525
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China