

## Plenco 504 Black (COM) Heat Resistant Mineral/Cellulose Filled Phenolic Molding Compound (discontinued \*\*)<

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Phenolic , Phenolic, Novolac, Heat Resistant Grade, Filled

### Material Notes:

Plaslok 504 is a two-stage, mineral and cellulose-filled phenolic molding compound having better impact and heat resistance than general purpose molding compounds. Since it also has good electrical properties, it has found use in a wide variety of wiring device applications. Data provided by Plaslok Corporation. Plaslok Corporation was purchased by Plastics Engineering Company in March 2000. The Plaslok name is no longer used on any products.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Plenco-504-Black-COM-Heat-Resistant-MineralCellulose-Filled-Phenolic-Molding-Compound-nbspdiscontinued-It.php](http://www.lookpolymers.com/polymer_Plenco-504-Black-COM-Heat-Resistant-MineralCellulose-Filled-Phenolic-Molding-Compound-nbspdiscontinued-It.php)

Physical Properties	Metric	English	Comments
Density	1.54 g/cc	0.0556 lb/in <sup>3</sup>	ASTM D792
Apparent Bulk Density	0.600 g/cc	0.0217 lb/in <sup>3</sup>	ASTM D1895
Water Absorption	0.20 %	0.20 %	ASTM D570
Linear Mold Shrinkage	0.0060 cm/cm	0.0060 in/in	Compression; ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	45.0 MPa	6530 psi	ASTM D638
Flexural Yield Strength	72.0 MPa	10400 psi	ASTM D790
Flexural Modulus	9.00 GPa	1310 ksi	ASTM D790
Compressive Yield Strength	221 MPa	32100 psi	ASTM D695

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	174 °C	345 °F	ASTM D648
UL RTI, Electrical	150 °C @Thickness 1.47 mm	302 °F @Thickness 0.0579 in	
UL RTI, Mechanical with Impact	150 °C @Thickness 1.47 mm	302 °F @Thickness 0.0579 in	
UL RTI, Mechanical without Impact	150 °C @Thickness 1.47 mm	302 °F @Thickness 0.0579 in	
Flammability, UL94	V-0	V-0	

Thermal Properties	@Thickness 1.47 mm Metric	@Thickness 0.0579 in English	Comments
	V-0	V-0	
	@Thickness 1.47 mm	@Thickness 0.0579 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	ASTM D257
Dielectric Constant	5.0	5.0	ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	7.0	7.0	ASTM D150
	@Frequency 60 Hz	@Frequency 60 Hz	
Dielectric Strength	15.7 kV/mm	399 kV/in	ASTM D149
Dissipation Factor	0.040	0.040	ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dissipation Factor	0.090	0.090	ASTM D150
	@Frequency 60 Hz	@Frequency 60 Hz	
Comparative Tracking Index	180 V	180 V	UL 746

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China