

Polimeri Europa Riblene® FC 26 Low Density Polyethylene - Blown Film Extrusion

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Film Grade

Material Notes:

Riblene FC 26 is a high molecular weight low density polyethylene (LDPE), with added antiblocking agent, suitable for blown film extrusion. Riblene FC 26 is characterized by a high melt strength leading to a good bubble stability during extrusion. Films manufactured with Riblene FC 26 are easily heat shrinkable and characterized by optimum mechanical properties. Main Applications: Riblene FC 26 is recommended for the production of heavy duty shrink film and industrial bags. Information provided by Polimeri Europa.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polimeri-Europa-Riblene-FC-26-Low-Density-Polyethylene-Blown-Film-Extrusion.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.922 g/cc	0.922 g/cc	ISO 1183
Thickness	50.0 - 250 microns	1.97 - 9.84 mil	Recommended
Melt Flow	0.25 g/10 min @Load 2.16 kg, Temperature 190 °C	0.25 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	10.0 MPa	1450 psi	ISO 527-3
Film Tensile Strength at Yield, TD	11.0 MPa	1600 psi	ISO 527-3
Film Elongation at Break, MD	350 %	350 %	ISO 527-3
Film Elongation at Break, TD	550 %	550 %	ISO 527-3
Coefficient of Friction, Dynamic	>= 0.50	>= 0.50	ISO 8295
Elmendorf Tear Strength, MD	2.038 g/micron	51.77 g/mil	ISO 6383-2
Elmendorf Tear Strength, TD	3.5665 g/micron	90.589 g/mil	ISO 6383-2
Dart Drop Test	225 g	0.496 lb	F50; ISO 7765-1
Film Tensile Strength at Break, MD	25.0 MPa	3630 psi	ISO 527-3
Film Tensile Strength at Break, TD	24.0 MPa	3480 psi	ISO 527-3
1% Secant Modulus, MD	180 MPa	26100 psi	ISO 527-3
1% Secant Modulus, TD	190 MPa	27600 psi	ISO 527-3

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
Vicat Softening Point	93.0 °C	199 °F	ISO 306/A
	@Load 1.00 kg	@Load 2.20 lb	
Brittleness Temperature	<= -75.0 °C	<= -103 °F	ASTM D746

Optical Properties	Metric	English	Comments
Haze	20 %	20 %	ISO 14782
Gloss	30 %	30 %	45°; ASTM D2457

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China