

PolyOne Dynaflex™ G7630-1 (Natural) Thermoplastic Elastomer (TPE)

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

Dynaflex™ G7630-1 (Natural) is an easy processing, general purpose TPE designed for a wide variety of applications, including those where FDA compliance is required. - Non-Slip Grip - Overmold Adhesion to Polypropylene - Soft Touch, Rubbery Feel Color concentrates with polypropylene (PP), ethylene vinyl acetate (EVA), or low density polyethylene (PE) carriers are most suitable for coloring Dynaflex™ G7630-1 (Natural). Improved color dispersion can be achieved by using higher melt flow concentrates (with a melt flow from 25 - 40 g/10 min). Typical loadings for color concentrates are 1% to 5% by weight. Liquid color can be used, but mineral oil based carriers may have a significant effect on the final hardness value. Concentrates based on PVC should not be used. A high color match consistency can be obtained by using precolored compounds available from GLS. The final determination of color concentrate suitability should be determined by customer trials. Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP). Re grind levels up to 20% can be used with Dynaflex™ G7630-1 (Natural) with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer. Dynaflex™ G7630-1 (Natural) has excellent melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer Drying is not Required Injection Speed: 1 to 3 in/sec 1st Stage - Boost Pressure: 200 to 900 psi 2nd Stage - Hold Pressure: 50% of Boost Hold Time (Thick Part): 3 to 10 sec Hold Time (Thin Part): 1 to 3 sec Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Dynaflex-G7630-1-Natural-Thermoplastic-Elastomer-TPE.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	ASTM D792
Viscosity	6400 cP @Shear Rate 11200 1/s, Temperature 200 °C	6400 cP @Shear Rate 11200 1/s, Temperature 392 °F	ASTM D3835
Linear Mold Shrinkage, Flow	0.013 - 0.021 cm/cm	0.013 - 0.021 in/in	ASTM D955
Melt Flow	31 g/10 min @Load 5.00 kg, Temperature 200 °C	31 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	29	29	10 sec; ASTM D2240
Tensile Strength at Break	3.28 MPa @Temperature 23.0 °C	476 psi @Temperature 73.4 °F	Die C2 hr; ASTM D412
Tensile Stress	0.689 MPa @Strain 100 %,	99.9 psi @Strain 100 %,	Die C2 hr; ASTM D412

Mechanical Properties	Temperature 23.0 °C Metric	Temperature 73.4 °F English	Comments
	1.65 MPa	239 psi	
	@Strain 300 %, Temperature 23.0 °C	@Strain 300 %, Temperature 73.4 °F	Die C2 hr; ASTM D412
Elongation at Break	650 %	650 %	
	@Temperature 23.0 °C	@Temperature 73.4 °F	Die C2 hr; ASTM D412
Tear Strength	14.9 kN/m	85.0 pli	ASTM D624
Compression Set	13 %	13 %	
	@Temperature 23.0 °C, Time 79200 sec	@Temperature 73.4 °F, Time 22.0 hour	ASTM D395B

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	160 - 188 °C	320 - 370 °F	
Middle Barrel Temperature	177 - 193 °C	351 - 379 °F	
Front Barrel Temperature	188 - 210 °C	370 - 410 °F	
Nozzle Temperature	188 - 216 °C	370 - 421 °F	
Mold Temperature	15.6 - 37.8 °C	60.1 - 100 °F	
Back Pressure	0.000 - 0.827 MPa	0.000 - 120 psi	
Screw Speed	40 - 100 rpm	40 - 100 rpm	

Descriptive Properties	Value	Comments
Agency Ratings	FDA 21 CFR 177.1210	Please contact GLS Thermoplastic Elastomers for a copy of the FDA compliance letter.
Appearance	Natural Color	
Features	General Purpose	
	Good Colorability	
	Good Flow	
	Good Processability	
	Good Processing Stability	
Forms	Pellets	
Generic Material	TPE	

Generic Name Descriptive Properties	Thermoplastic Elastomer Value (TPE)	Comments
Manufacturer / Supplier	GLS Thermoplastic Elastomers	
Processing Method	Extrusion	
	Injection Molding	
Regional Availability	Asia Pacific	
RoHS Compliance	RoHS Compliant	
Suggested Max Regrind	20%	
Uses	Consumer Applications	
	Flexible Grips	
	Gaskets	
	General Purpose	
	Overmolding	
	Seals	
	Soft Touch Applications	
	Sporting Goods	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China