

PolyOne Edgetek® MLS-20GF/000 Polysulfone Alloy - 20% Glass Fiber Reinforced (discontinued **)

Category : Polymer , Thermoplastic , Polysulfone (PSU)

Material Notes:

Data provided by PolyOne.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Edgetek-MLS-20GF000-Polysulfone-Alloy-20-Glass-Fiber-Reinforced-nbspdiscontinued.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.36 g/cc	1.36 g/cc	ASTM D792
Water Absorption	0.16 % @Thickness 3.17 mm	0.16 % @Thickness 0.125 in	24 hr. Immersion; ASTM D570
Linear Mold Shrinkage	0.0030 - 0.0040 cm/cm	0.0030 - 0.0040 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	103 MPa	15000 psi	Type 1 - Rigids, Yield, 0.2 in/min; ASTM D638
Elongation at Break	3.0 - 4.0 %	3.0 - 4.0 %	Type 1 - Rigids, 0.2 in/min; ASTM D638
Tensile Modulus	4.96 GPa	720 ksi	Type 1 - Rigids, 0.2 in/min; ASTM D638
Flexural Strength	124 MPa	18000 psi	ASTM D790
Flexural Modulus	4.76 GPa	690 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm @Thickness 3.17 mm, Temperature 23.0 °C	2.00 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Method A, Injection Molded; ASTM D256

Processing Properties	Metric	English	Comments
Melt Temperature	332 - 349 °C	630 - 660 °F	Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China