

PolyOne Edgetek® NN-30GF/000 Polyamide 66 (Nylon 66)

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

The Edgetek® Engineering Thermoplastic Compounds portfolio covers a broad range of standard and custom-formulated high performance materials. This portfolio includes high-temperature materials for elevated service temperature environments, high-modulus / structural materials for load-bearing and high-strength applications and flame-retardant products. These compounds are based on select engineering thermoplastic resins that are compounded with reinforcing additives such as carbon fiber, glass fiber and glass beads. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Edgetek-NN-30GF000-Polyamide-66-Nylon-66.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.37 g/cc	1.37 g/cc	ASTM D792
Water Absorption	0.70 % @Thickness 0.508 mm	0.70 % @Thickness 0.0200 in	@ 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	172 MPa	24900 psi	Type I, 5.1 mm/min; ASTM D638
Elongation at Break	4.0 %	4.0 %	Type I, 5.1 mm/min; ASTM D638
Tensile Modulus	8.27 GPa	1200 ksi	Type I, 5.1 mm/min; ASTM D638
Flexural Strength	290 MPa	42100 psi	ASTM D790
Flexural Modulus	8.27 GPa	1200 ksi	ASTM D790
Izod Impact, Notched	0.960 J/cm @Thickness 6.35 mm, Temperature 23.0 °C	1.80 ft-lb/in @Thickness 0.250 in, Temperature 73.4 °F	Injection Molded; ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	252 °C @Thickness 3.18 mm	486 °F @Thickness 0.125 in	Annealed; ASTM D648
Flammability, UL94	HB	HB	UL 94

Processing Properties	Metric	English	Comments
Melt Temperature	277 - 299 °C	531 - 570 °F	

Processing Properties	Metric 121 °C	English 250 °F	Comments
Drying Temperature	71.1 - 82.2 °C	160 - 180 °F	
Dry Time	2.00 hour	2.00 hour	

Descriptive Properties	Value	Comments
Filler / Reinforcement	Glass Fiber Reinforcement, 30% Filler by Weight	
Forms	Pellets	
Generic Material	Nylon 66	
Generic Name	Polyamide 66 (Nylon 66)	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
RoHS Compliance	RoHS Compliant	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China