

PolyOne Edgetek® SF-20CF/000 Polyphenylene Sulfide (PPS) (discontinued **)

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS)

Material Notes:

The Edgetek® Engineering Thermoplastic Compounds portfolio covers a broad range of standard and custom-formulated high performance materials. This portfolio includes high-temperature materials for elevated service temperature environments, high-modulus / structural materials for load-bearing and high-strength applications and flame-retardant products. These compounds are based on select engineering thermoplastic resins that are compounded with reinforcing additives such as carbon fiber, glass fiber and glass beads. Description/Features: PPS (Polyphenylenesulfide) 20% Carbon Fiber Reinforced Hi-Temp Applications: Multi-Purpose Processing Method: Injection Molding Information provided by PolyOne Corporation

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Edgetek-SF-20CF000-Polyphenylene-Sulfide-PPS-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	ASTM D792
Water Absorption	0.040 % @Thickness 3.17 mm	0.040 % @Thickness 0.125 in	24 hr. Immersion; ASTM D570
Linear Mold Shrinkage	0.0010 - 0.0020 cm/cm	0.0010 - 0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	159 MPa	23000 psi	Type 1 - Rigids, Yield, 0.2 in/min; ASTM D638
Elongation at Break	2.0 - 3.0 %	2.0 - 3.0 %	Type 1 - Rigids, 0.2 in/min; ASTM D638
Tensile Modulus	15.2 GPa	2200 ksi	Type 1 - Rigids, 0.2 in/min; ASTM D638
Flexural Strength	221 MPa	32000 psi	ASTM D790
Flexural Modulus	15.2 GPa	2200 ksi	ASTM D790
Izod Impact, Notched	0.641 J/cm @Thickness 3.17 mm, Temperature 23.0 °C	1.20 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Method A, Injection Molded; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	260 °C	500 °F	Unannealed; ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	316 - 327 °C	600 - 620 °F	Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China