

PolyOne Geon™ HTX Ultra LA426 Gray 2382 Polyvinyl Chloride Alloy (PVC Alloy)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Optimum for Black and Darker Colors between 50 and 70 L value. Also suitable for colors above 70 L value. Recommend drying material for a minimum of 2 hours at 160 degrees Fahrenheit. Physical properties based on Geon HTX Ultra LA426 Gray 2382 Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-HTX-Ultra-LA426-Gray-2382-Polyvinyl-Chloride-Alloy-PVC-Alloy.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 g/cc	1.25 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	75	75	15 sec; ASTM D2240
Tensile Strength, Yield	35.2 MPa	5110 psi	Type I, 5.1 mm/min; ASTM D638
Tensile Modulus	1.90 GPa	276 ksi	Type I, 5.1 mm/min; ASTM D638
Flexural Strength	61.9 MPa	8980 psi	ASTM D790
Flexural Modulus	1.91 GPa	277 ksi	ASTM D790
Izod Impact, Notched	7.20 J/cm @Thickness 3.18 mm, Temperature 23.0 °C	13.5 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Compression Molded; ASTM D256A
Dart Drop Total Energy	59.6 J/cm @Temperature 23.0 °C	0.112 ft-lb/mil @Temperature 73.4 °F	Procedure A, C.125; ASTM D4226
	178 J/cm @Temperature 23.0 °C	0.333 ft-lb/mil @Temperature 73.4 °F	Procedure B, C.125; ASTM D4226

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	84.0 µm/m-°C	46.7 µin/in-°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	90.0 °C @Thickness 3.18 mm	194 °F @Thickness 0.125 in	Unannealed; ASTM D648
	91.1 °C @Thickness 3.18 mm	196 °F @Thickness 0.125 in	Annealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	83.3 °C	182 °F	Unannealed; ASTM D648

Thermal Properties	@Thickness 3.18 mm Metric	@Thickness 0.125 in English	Comments
	86.7 °C	188 °F	Annealed; ASTM D648
	@Thickness 3.18 mm	@Thickness 0.125 in	

Processing Properties	Metric	English	Comments
Melt Temperature	174 - 193 °C	345 - 379 °F	

Descriptive Properties	Value	Comments
Ease of Sizing	Acceptable	
Features	High Impact Resistance	
	High Stiffness	
Forms	Pellets	
Generic Material	PVC Alloy	
Generic Name	Polyvinyl Chloride Alloy (PVC Alloy)	
Processing Method	Extrusion	
PVC Cell Classification	15215	ASTM D1784
	4-41410-64-0000	ASTM D4216
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Outdoor Applications	
	Profiles	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China