

## PolyOne Geon™ Vinyl Flexible A9000 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

### Material Notes:

Recommended for interior applications. Information provided by PolyOne

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Geon-Vinyl-Flexible-A9000-Polyvinyl-Chloride-Flexible-PVC-Flexible.php](http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-A9000-Polyvinyl-Chloride-Flexible-PVC-Flexible.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.013 - 0.017 cm/cm	0.013 - 0.017 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	84	84	15 sec; ASTM D2240
	90	90	ASTM D2240
Tensile Strength at Break	18.6 MPa	2700 psi	510 mm/min; ASTM D638
Tensile Strength	10.9 MPa @Strain 100 %	1580 psi @Strain 100 %	510 mm/min; ASTM D638
Elongation at Break	390 %	390 %	510 mm/min; ASTM D638
Tear Strength	85.8 kN/m	490 pli	Die C, 510 mm/min; ASTM D624
Compression Set	37 % @Temperature 23.0 °C, Time 79200 sec	37 % @Temperature 73.4 °F, Time 22.0 hour	ASTM D395
Clash Berg Modulus	0.545 GPa	79.0 ksi	ASTM D1043
	0.310 GPa @Temperature -24.0 °C	45.0 ksi @Temperature -11.2 °F	ASTM D1043

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-33.9 °C	-29.0 °F	ASTM D746

Optical Properties	Metric	English	Comments
Haze	5.0 % @Thickness 1.91 mm	5.0 % @Thickness 0.0750 in	ASTM D1003
	80 %	80 %	

Transmission Visible Optical Properties	Metric @ Thickness 1.91 mm	English @ Thickness 0.0750 in	ASTM D1003 Comments
--	-------------------------------	----------------------------------	------------------------

Processing Properties	Metric	English	Comments
Melt Temperature	177 - 182 °C	351 - 360 °F	
	193 - 204 °C	379 - 399 °F	

Descriptive Properties	Value	Comments
Agency Ratings	NSF 51	Trans 9000 and Trans 9400. Max. Temperature of use = 100 degrees F.
Appearance	Clear/Transparent	
Features	General Purpose	
	High Gloss	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	
	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Film	
	General Purpose	
	Hose	
	Sheet	
	Tubing	

**Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**