

PolyOne Geon™ Vinyl Flexible D75M0 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-D75M0-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.45 g/cc	1.45 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	66	66	15 sec; ASTM D2240
	75	75	ASTM D2240
Tensile Strength at Break	11.0 MPa	1600 psi	510 mm/min; ASTM D638
Tensile Strength	4.48 MPa	650 psi	510 mm/min; ASTM D638
	@Strain 100 %	@Strain 100 %	
Elongation at Break	400 %	400 %	510 mm/min; ASTM D638
Tear Strength	40.3 kN/m	230 pli	Die C, 510 mm/min; ASTM D624
Compression Set	19 %	19 %	ASTM D395
	@Temperature 23.0 °C, Time 79200 sec	@Temperature 73.4 °F, Time 22.0 hour	
Clash Berg Modulus	0.827 GPa	120 ksi	ASTM D1043
	0.310 GPa	45.0 ksi	ASTM D1043
	@Temperature -28.0 °C	@Temperature -18.4 °F	

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-21.7 °C	-7.06 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	171 - 177 °C	340 - 351 °F	

Descriptive Properties	Value	Comments
Features	Low Gloss	

Descriptive Properties	Value	Comments
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China