

PolyOne Geon™ Vinyl Flexible R7543E Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Typical Properties of Molded Slab (0.075); Not to be Construed as Specifications. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-R7543E-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.49 g/cc	1.49 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	87	87	15 sec; ASTM D2240
Tensile Strength, Yield	15.9 MPa	2310 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	300 %	300 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-33.0 °C	-27.4 °F	ASTM D746
Oxygen Index	28 % @Thickness 1.91 mm	28 % @Thickness 0.0752 in	ASTM D2863

Processing Properties	Metric	English	Comments
Melt Temperature	165 - 175 °C	329 - 347 °F	

Descriptive Properties	Value	Comments
Additive	Lead Stabilizer	
Agency Ratings	CSA LAG (Low Acid Gas)	
Features	Flame Retardant	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
HCL Evolution	12%	CSA C22.2 No. 0.3
Processing Method	Extrusion Coating	

Descriptive Properties Regional Availability	Value Africa & Middle East	Comments
	Asia Pacific	
	Europe	
	North America	
	South America	
Retention of Tensile Elongation	80%	121°C, 1.91 mm; 336 hr, UL Standard
Retention of Tensile Strength	97%	121°C, 1.91 mm; 336 hr, UL Standard
Uses	Cable Jacketing	
	Wire & Cable Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China