

## PolyOne Geon™ Vinyl Flexible R8570B Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

**Material Notes:**

Information provided by PolyOne

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Geon-Vinyl-Flexible-R8570B-Polyvinyl-Chloride-Flexible-PVC-Flexible.php](http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-R8570B-Polyvinyl-Chloride-Flexible-PVC-Flexible.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.51 g/cc	1.51 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	88	88	15 sec; ASTM D2240
Tensile Strength at Break	15.0 MPa	2180 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	250 %	250 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-10.0 °C	14.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	177 - 182 °C	351 - 360 °F	

Descriptive Properties	Value	Comments
Features	Low Gloss	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	
	Profile Extrusion	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	

Descriptive Properties	North America Value	Comments
	South America	
Uses	Automotive Applications	
	Automotive Exterior Trim	
	Profiles	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China