

## PolyOne Geon™ Vinyl Flexible SL60 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

### Material Notes:

Information provided by PolyOne

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Geon-Vinyl-Flexible-SL60-Polyvinyl-Chloride-Flexible-PVC-Flexible.php](http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-SL60-Polyvinyl-Chloride-Flexible-PVC-Flexible.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.33 g/cc	1.33 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	61	61	15 sec; ASTM D2240
Tensile Strength at Break	12.1 MPa	1750 psi	Type IV, 510 mm/min; ASTM D638
Tensile Strength	4.14 MPa @Strain 100 %	600 psi @Strain 100 %	Type IV, 510 mm/min; ASTM D638
Elongation at Break	350 %	350 %	Type IV, 510 mm/min; ASTM D638
Tear Strength	35.0 kN/m	200 pli	Die C, 510 mm/min; ASTM D624

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-42.2 °C	-44.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	166 - 171 °C	331 - 340 °F	
	188 - 199 °C	370 - 390 °F	

Descriptive Properties	Value	Comments
Additive	Biocide	
	UV Stabilizer	
Features	Medium Gloss	
	UV Absorbing	
Forms	Pellets	
Generic Material	PVC, Flexible	

Generic Name Descriptive Properties	Polyvinyl Chloride, Flexible (PVC, Flexible) Value	Comments
Processing Method	Extrusion	
	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Bathroom Accessories	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China