

PolyOne Geon™ Vinyl Rigid Extrusion 87547 Polyvinyl Chloride, Rigid (PVC, Rigid)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Rigid Grade

Material Notes:

The Cell Classification was determined using the notched Izod test with injection molded samples. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Rigid-Extrusion-87547-Polyvinyl-Chloride-Rigid-PVC-Rigid.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.33 g/cc	1.33 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	82	82	15 sec; ASTM D2240
Tensile Strength, Yield	53.4 MPa	7750 psi	Type I, 5.1 mm/min; ASTM D638
Tensile Modulus	2.79 GPa	405 ksi	Type I, 5.1 mm/min; ASTM D638
Flexural Strength	88.5 MPa	12800 psi	ASTM D790
Flexural Modulus	2.84 GPa	412 ksi	ASTM D790
Izod Impact, Notched	1.40 J/cm	2.62 ft-lb/in	Compression Molded, Flow; ASTM D256A
	@Thickness 3.18 mm, Temperature 23.0 °C	@Thickness 0.125 in, Temperature 73.4 °F	
	5.70 J/cm	10.7 ft-lb/in	Compression Molded, Across Flow; ASTM D256A
Dart Drop Total Energy	11.0 J/cm	20.6 ft-lb/in	Injection Molded; ASTM D256A
	@Thickness 3.18 mm, Temperature 23.0 °C	@Thickness 0.125 in, Temperature 73.4 °F	
	52.0 J/cm	0.0974 ft-lb/mil	Procedure A, C.125; ASTM D4226
Dart Drop Total Energy	173 J/cm	0.324 ft-lb/mil	Procedure B, C.125; ASTM D4226
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 µm/m-°C	38.9 µin/in-°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	67.2 °C	153 °F	Unannealed; ASTM D648

Thermal Properties	@Thickness 3.18 mm Metric	@Thickness 0.125 in English	Comments
Processing Properties	Metric	English	Comments
Melt Temperature	182 - 193 °C	360 - 379 °F	

Descriptive Properties	Value	Comments
Appearance	Clear/Transparent	
Features	High Flow	
	High Impact Resistance	
Forms	Pellets	
Generic Material	PVC, Rigid	
Generic Name	Polyvinyl Chloride, Rigid (PVC, Rigid)	
Processing Method	Extrusion	
PVC Cell Classification	16453	ASTM D1784
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Profiles	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China