

## PolyOne Gravi-Tech™ GRV-NP-069-BMX Nylon 12 (discontinued \*\*)

Category : Polymer , Thermoplastic , Nylon , Nylon 12

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Gravi-Tech-GRV-NP-069-BMX-Nylon-12-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_PolyOne-Gravi-Tech-GRV-NP-069-BMX-Nylon-12-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Specific Gravity	6.88 g/cc	6.88 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0050 - 0.0060 cm/cm	0.0050 - 0.0060 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	44.8 MPa	6500 psi	Type I, 5.1 mm/min; ASTM D638
Elongation at Break	1.8 %	1.8 %	Type I, 5.1 mm/min; ASTM D638
Tensile Modulus	7.58 GPa	1100 ksi	Type I, 5.1 mm/min; ASTM D638
Flexural Modulus	4.96 GPa	719 ksi	ASTM D790
Izod Impact, Notched	1.12 J/cm @Thickness 6.35 mm, Temperature 23.0 °C	2.10 ft-lb/in @Thickness 0.250 in, Temperature 73.4 °F	Injection Molded; ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	159 °C @Thickness 6.35 mm	318 °F @Thickness 0.250 in	Unannealed; ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	260 - 288 °C	500 - 550 °F	
Mold Temperature	82.2 - 149 °C	180 - 300 °F	
Drying Temperature	79.4 °C @Time 14400 sec	175 °F @Time 4.00 hour	

Descriptive Properties	Value	Comments
Features	Non-Toxic	
Forms	Pellets	
Generic Name	Polyamide 12 (Nylon 12)	

<b>Processing Method</b> Descriptive Properties	<b>Injection Molding</b> Value	Comments
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Industrial Applications	
	Medical/Healthcare Applications	
	Projectiles	
	Radiation Shielding	
	Sporting Goods	
	Weighting & Balancing	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China