

## PolyOne Nymax™ GF 1800 33 BLACK 13 Nylon 612 with 33% Glass Fiber (discontinued \*\*)

Category : Polymer , Thermoplastic , Nylon , Nylon 612 , Nylon 612, Glass Fiber Filler

### Material Notes:

Molded Test Bars: Dry as Molded

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Nymax-GF-1800-33-BLACK-13-Nylon-612-with-33-Glass-Fiber-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_PolyOne-Nymax-GF-1800-33-BLACK-13-Nylon-612-with-33-Glass-Fiber-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.32 g/cc	1.32 g/cc	ASTM D792
Filler Content	33 %	33 %	
Water Absorption	0.20 % @Thickness 3.18 mm, Time 86400 sec	0.20 % @Thickness 0.125 in, Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0020 cm/cm	0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	148 MPa	21500 psi	Type I, 5.1 mm/min; ASTM D638
Elongation at Break	4.0 %	4.0 %	Type I, 5.1 mm/min; ASTM D638
Flexural Modulus	7.58 GPa	1100 ksi	ASTM D790
Izod Impact, Notched	1.01 J/cm @Thickness 3.18 mm, Temperature 23.0 °C	1.89 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Injection Molded; ASTM D256A

Thermal Properties	Metric	English	Comments
Melting Point	215 °C	419 °F	ASTM D789
Deflection Temperature at 1.8 MPa (264 psi)	193 °C @Thickness 3.18 mm	379 °F @Thickness 0.125 in	Unannealed; ASTM D648

Descriptive Properties	Value	Comments
Appearance	Black	
Forms	Pellets	
Generic Name	Polyamide 612 (Nylon 6/12)	
Regional Availability	North America	

Descriptive Properties	Value South America	Comments
------------------------	------------------------	----------

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China