

PolyOne Stat-Tech™ AT-10CF/000 Acetal (POM) Copolymer

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

Material Notes:

Stat-Tech™ Electrically Conductive Compounds are specifically engineered to provide anti-static, ESD and RFI/EMI shielding performance for critical electronic equipment applications. These compounds combine the performance of select engineering resins with reinforcing additives such as carbon powder, carbon fiber, nickel-coated carbon fiber and stainless steel fiber, for low to high levels of conductivity depending upon application requirements. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Stat-Tech-AT-10CF000-Acetal-POM-Copolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.43 g/cc	1.43 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.022 - 0.026 cm/cm	0.022 - 0.026 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	62.3 MPa	9040 psi	ASTM D638
Elongation at Break	2.3 %	2.3 %	Type I, 5.1 mm/min; ASTM D638
Tensile Modulus	11.7 GPa	1700 ksi	Type I, 5.1 mm/min; ASTM D638
Flexural Strength	107 MPa	15500 psi	ASTM D790
Flexural Modulus	7.38 GPa	1070 ksi	ASTM D790
Izod Impact, Notched	0.370 J/cm @Thickness 3.18 mm, Temperature 23.0 °C	0.693 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Injection Molded; ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	161 °C @Thickness 6.35 mm	322 °F @Thickness 0.250 in	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	141 °C @Thickness 6.35 mm	286 °F @Thickness 0.250 in	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	100 - 10000 ohm-cm	100 - 10000 ohm-cm	ASTM D257
Surface Resistance	100 - 10000 ohm	100 - 10000 ohm	ASTM D257

Electrical Properties	Metric	English	Comments
Static Decay	0.0030 sec	0.0030 sec	(MI: W-81705C), 12% RH, 5000 kV to 50 kV

Processing Properties	Metric	English	Comments
Melt Temperature	199 - 210 °C	390 - 410 °F	

Descriptive Properties	Value	Comments
Features	Antistatic	
	Conductive	
	Electrically Conductive	
	Statically Conductive	
Filler / Reinforcement	Carbon Fiber Reinforcement, 10% Filler by Weight	
Forms	Pellets	
Generic Material	Acetal (POM) Copolymer	
Generic Name	Acetal (POM) Copolymer	
Processing Method	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
RoHS Compliance	RoHS Compliant	
Uses	Aerospace Applications	
	Automotive Electronics	
	Business Equipment	
	Computer Components	
	Connectors	
	Electrical Housing	
	Electrical/Electronic Applications	

Descriptive Properties	Housings Value	Comments
------------------------	-------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China