

PolyOne Therma-Tech™ NJC-6000 TC Nylon 12 (discontinued **)

Category : Polymer , Thermoplastic , Nylon , Nylon 12

Material Notes:

Therma-Tech™ Thermal Management Compounds have been engineered to combine the heat transfer and cooling capabilities of metals with the design freedom, weight reduction and cost advantages of thermoplastics. These materials provide the benefits of proprietary conductive additive technologies and the performance of select engineering thermoplastic resins. Therma-Tech compounds have been shown to improve thermal conductivity up to 100-times that of conventional plastics and can be used in a wide range of thermal management applications.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Therma-Tech-NJC-6000-TC-Nylon-12-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.58 g/cc	1.58 g/cc	ASTM D792
Water Absorption	0.10 %	0.10 %	ASTM D570
	@Thickness 3.18 mm, Time 86400 sec	@Thickness 0.125 in, Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0030 - 0.0040 cm/cm	0.0030 - 0.0040 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	49.0 MPa	7110 psi	Type I, 5.1 mm/min; ASTM D638
Elongation at Break	0.90 %	0.90 %	Type I, 5.1 mm/min; ASTM D638
Tensile Modulus	19.3 GPa	2800 ksi	Type I, 5.1 mm/min; ASTM D638
Flexural Strength	103 MPa	14900 psi	ASTM D790
Flexural Modulus	19.4 GPa	2810 ksi	ASTM D790
Izod Impact, Notched	0.267 J/cm	0.500 ft-lb/in	Injection Molded; ASTM D256A
	@Thickness 6.35 mm, Temperature 23.0 °C	@Thickness 0.250 in, Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	11.0 W/m-K	76.3 BTU-in/hr-ft ² -°F	ASTM C177
Deflection Temperature at 0.46 MPa (66 psi)	193 °C	379 °F	Unannealed; ASTM D648
	@Thickness 6.35 mm	@Thickness 0.250 in	
Deflection Temperature at 1.8 MPa (264 psi)	185 °C	365 °F	Unannealed; ASTM D648
	@Thickness 6.35 mm	@Thickness 0.250 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	100 - 1000 ohm-cm	100 - 1000 ohm-cm	ASTM D257
Surface Resistance	10 - 100 ohm	10 - 100 ohm	ASTM D257

Processing Properties	Metric	English	Comments
Melt Temperature	260 - 277 °C	500 - 531 °F	
Mold Temperature	65.6 - 93.3 °C	150 - 200 °F	

Descriptive Properties	Value	Comments
Features	Electrically Conductive	
	Thermally Conductive	
Forms	Pellets	
Generic Name	Polyamide 12 (Nylon 12)	
Processing Method	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Automotive Applications	
	Automotive Under the Hood	
	Consumer Applications	
	Electrical/Electronic Applications	
	Housings	
	Industrial Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China