

PolyOne Versollan™ OM 1262NX-9 Thermoplastic Elastomer (TPE)

Category : Polymer , Thermoplastic , Elastomer , TPE

Material Notes:

Versollan™ OM 1262NX-9 is a performance TPU alloy designed for thin-wall overmolding onto polycarbonate (PC), ABS, PC/ABS and copolyester substrates. - Excellent Grip with Matte, Rubbery Finish - Proven Track Record - Superior Adhesion to PC, ABS, PC/ABS, PC/PBT and CopolyesterPurge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP). Regrind levels up to 20% can be used with Versollan™ OM 1262NX-9 with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer. Versollan™ OM 1262NX-9 should not be left in the barrel for extended idle periods (greater than 5 minutes). Suggested Dewpoint: -40°F Injection Speed: 1 to 5 in/sec 1st Stage - Boost Pressure: 200 to 800 psi 2nd Stage - Hold Pressure: 70% of Boost Hold Time (Thick Part): 4 to 10 sec Hold Time (Thin Part): 1 to 3 secInformation provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Versollan-OM-1262NX-9-Thermoplastic-Elastomer-TPE.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.17 g/cc	1.17 g/cc	ASTM D792
Viscosity	19900 cP	19900 cP	ASTM D3835
	@Shear Rate 11200 1/s, Temperature 200 °C	@Shear Rate 11200 1/s, Temperature 392 °F	
Maximum Moisture Content	0.020 - 0.030	0.020 - 0.030	
Linear Mold Shrinkage, Flow	0.0090 - 0.015 cm/cm	0.0090 - 0.015 in/in	ASTM D955
Melt Flow	7.0 g/10 min	7.0 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	
	100 g/10 min	100 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	10 sec; ASTM D2240
Tensile Strength at Break	7.64 MPa	1110 psi	Die C2 hr; ASTM D412
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Tensile Stress	2.55 MPa	370 psi	Die C2 hr; ASTM D412
	@Strain 100 %, Temperature 23.0 °C	@Strain 100 %, Temperature 73.4 °F	

Mechanical Properties	3.34 MPa Metric	484 psi English	Comments Die C2 hr; ASTM D412
	@Strain 300 %, Temperature 23.0 °C	@Strain 300 %, Temperature 73.4 °F	
Elongation at Break	710 % @Temperature 23.0 °C	710 % @Temperature 73.4 °F	Die C2 hr; ASTM D412
Tear Strength	40.3 kN/m	230 pli	ASTM D624
Compression Set	35 % @Temperature 23.0 °C, Time 79200 sec	35 % @Temperature 73.4 °F, Time 22.0 hour	ASTM D395B

Thermal Properties	Metric	English	Comments
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	UL 94

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	163 - 185 °C	325 - 365 °F	
Middle Barrel Temperature	168 - 196 °C	334 - 385 °F	
Front Barrel Temperature	177 - 210 °C	351 - 410 °F	
Nozzle Temperature	177 - 210 °C	351 - 410 °F	
Mold Temperature	21.1 - 48.9 °C	70.0 - 120 °F	
Drying Temperature	51.7 - 54.4 °C	125 - 130 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	
Back Pressure	0.172 - 0.345 MPa	24.9 - 50.0 psi	
Screw Speed	25 - 75 rpm	25 - 75 rpm	

Descriptive Properties	Value	Comments
Agency Ratings	UL 94 .QMFZ2.E76261	
Appearance	Black	
Features	Good Moldability	
	Good Processability	
	Low Gloss	
Forms	Pellets	

Descriptive Properties	Value	Comments
Generic Name	Thermoplastic Elastomer (TPE)	
Manufacturer / Supplier	GLS Thermoplastic Elastomers	
Processing Method	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
RoHS Compliance	RoHS Compliant	
Suggested Max Regrind	20%	
Uses	Business Equipment	
	Consumer Applications	
	Electrical/Electronic Applications	
	Flexible Grips	
	Overmolding	
	Power/Other Tools	
	Thin-walled Parts	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China