

Polykemi AB POLYfill PP EIP16020 F PP Mineral Reinforced, Extrusion Grade, Low CLTE

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Talc Filler , Polypropylene, Extrusion Grade

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-POLYfill-PP-EIP16020-F-PP-Mineral-Reinforced-Extrusion-Grade-Low-CLTE.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ISO 1183
Filler Content	20 %	20 %	±2%; Polykemi
Linear Mold Shrinkage	0.010 - 0.012 cm/cm	0.010 - 0.012 in/in	With Flow; ISO 2577
	0.010 - 0.012 cm/cm	0.010 - 0.012 in/in	Across Flow; ISO 2577
Melt Index of Compound	16 g/10 min @Load 2.16 kg, Temperature 230 °C	16 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 20.0 MPa	<= 2900 psi	ISO/R527
Elongation at Yield	6.0 %	6.0 %	ISO/R527
Flexural Strength	<= 34.0 MPa	<= 4930 psi	ISO 178
Flexural Modulus	1.70 GPa @Temperature 23.0 °C	247 ksi @Temperature 73.4 °F	ISO 178
Charpy Impact, Notched	0.300 J/cm ² @Temperature -20.0 °C	1.43 ft-lb/in ² @Temperature -4.00 °F	ISO 179
	1.00 J/cm ² @Temperature 23.0 °C	4.76 ft-lb/in ² @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	65.0 °C	149 °F	120°C/h; ISO 75/1
Vicat Softening Point	145 °C @Load 1.00 kg	293 °F @Load 2.21 lb	50°C/h; ISO 306
	HB	HB	

Thermal Properties	Metric	English	Comments
	@ Thickness 1.60 mm	@ Thickness 0.0630 in	
Glow Wire Test	750 °C	1380 °F	IEC 695-2-1
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Processing Properties	Metric	English	Comments
Melt Temperature	230 - 250 °C	446 - 482 °F	
Mold Temperature	30.0 - 60.0 °C	86.0 - 140 °F	
Drying Temperature	70.0 - 80.0 °C	158 - 176 °F	
Dry Time	2 - 4 hour	2 - 4 hour	in circulation dryer
	2 - 4 hour	2 - 4 hour	in desiccant air dryer
Injection Pressure	40.0 - 70.0 MPa	5800 - 10200 psi	
Back Pressure	0.500 - 1.50 MPa	72.5 - 218 psi	

Descriptive Properties	Value	Comments
Holding Pressure ()	20-40	% of injection pressure
Injection Speed ()	High	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China