

Polykemi AB POLYfill PPH TS15040 Polypropylene Homopolymer, Mineral Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Talc Filler

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-POLYfill-PPH-TS15040-Polypropylene-Homopolymer-Mineral-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.23 g/cc	0.0444 lb/in ³	ISO 1183
Filler Content	40 %	40 %	±2%; Polykemi
Linear Mold Shrinkage	0.0090 - 0.011 cm/cm	0.0090 - 0.011 in/in	With Flow; ISO 2577
	0.0090 - 0.011 cm/cm	0.0090 - 0.011 in/in	Across Flow; ISO 2577
Melt Index of Compound	15 g/10 min	15 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 28.0 MPa	<= 4060 psi	ISO/R527
Elongation at Yield	5.0 %	5.0 %	ISO/R527
Flexural Strength	<= 53.0 MPa	<= 7690 psi	ISO 178
Flexural Modulus	3.20 GPa	464 ksi	ISO 178
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.200 J/cm ²	0.952 ft-lb/in ²	ISO 179
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	0.300 J/cm ²	1.43 ft-lb/in ²	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	122 °C	252 °F	120°C/h; ISO 75/1
Deflection Temperature at 1.8 MPa (264 psi)	70.0 °C	158 °F	120°C/h; ISO 75/1
Vicat Softening Point	84.0 °C	183 °F	50°C/h; ISO 306

Thermal Properties	@Load 5.001 kg Metric	@Load 11.03 lb English	Comments
	146 °C	295 °F	50°C/h; ISO 306
	@Load 1.00 kg	@Load 2.21 lb	

Processing Properties	Metric	English	Comments
Melt Temperature	205 - 260 °C	401 - 500 °F	
Mold Temperature	40.0 - 80.0 °C	104 - 176 °F	
Drying Temperature	70.0 - 80.0 °C	158 - 176 °F	
Dry Time	2 - 4 hour	2 - 4 hour	in circulation dryer
	2 - 4 hour	2 - 4 hour	in desiccant air dryer
Injection Pressure	40.0 - 110 MPa	5800 - 16000 psi	
Back Pressure	1.00 - 2.00 MPa	145 - 290 psi	

Descriptive Properties	Value	Comments
Holding Pressure ()	20-40	% of injection pressure
Injection Speed ()	High	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China