

## Polykemi AB POLYform POM C M20 Polyoxymethylene

Category : Polymer , Thermoplastic

### Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polykemi-AB-POLYform-POM-C-M20-Polyoxymethylene.php](http://www.lookpolymers.com/polymer_Polykemi-AB-POLYform-POM-C-M20-Polyoxymethylene.php)

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage	0.018 - 0.020 cm/cm	0.018 - 0.020 in/in	With Flow; ISO 2577
	0.018 - 0.020 cm/cm	0.018 - 0.020 in/in	Across Flow; ISO 2577
Melt Index of Compound	2.0 g/10 min	2.0 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 60.0 MPa	<= 8700 psi	ISO/R527
Elongation at Yield	14 %	14 %	ISO/R527
Tensile Modulus	2.40 GPa	348 ksi	ISO 527
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Flexural Strength	<= 87.0 MPa	<= 12600 psi	ISO 178
Flexural Modulus	2.10 GPa	305 ksi	ISO 178
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.800 J/cm <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	120°C/h; ISO 75/1
Vicat Softening Point	150 °C	302 °F	50°C/h; ISO 306
	@Load 5.001 kg	@Load 11.03 lb	
	163 °C	325 °F	50°C/h; ISO 306
	@Load 1.00 kg	@Load 2.21 lb	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**