

## Polyplastics Duranex® 6300B Polybutylene Terephthalate (PBT), Anisotropy improvement, 30% GB filled

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Glass Bead Filled

### Material Notes:

DURANEX® is a crystalline thermoplastic based on polybutylene terephthalate (PBT) that can be readily strengthened, modified, or otherwise performance enhanced through the addition of glass fibers or other inorganic filler additives. Various grades are available, including flame-retardant, reinforced, and impact-resistant grades. DURANEX®, due to its mechanical strength, heat stability, electrical resistivity and wear and abrasion-resistance, offers great potential as a well-balanced, highly reliable material, having a wide variety of applications including electronic / electro-mechanical and automobile parts and various other functional parts. DURANEX® also assures moldability, dimensional stability, glossy surfaces and various fabrication capabilities providing higher added value. Information provided by PolyPlastics.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polyplastics-Duranex-6300B-Polybutylene-Terephthalate-PBT-Anisotropy-improvement-30-GB-filled.php](http://www.lookpolymers.com/polymer_Polyplastics-Duranex-6300B-Polybutylene-Terephthalate-PBT-Anisotropy-improvement-30-GB-filled.php)

Physical Properties	Metric	English	Comments
Density	1.53 g/cc	0.0553 lb/in <sup>3</sup>	ISO 1183
Filler Content	30 %	30 %	Glass bead

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	53.0 MPa	7690 psi	ISO 527-1, 2
Elongation at Break	2.5 %	2.5 %	ISO 527-1, 2
Flexural Strength	91.0 MPa	13200 psi	ISO 178
Flexural Modulus	3.90 GPa	566 ksi	ISO 178
Charpy Impact, Notched	0.200 J/cm <sup>2</sup>	0.952 ft-lb/in <sup>2</sup>	ISO 179/1eA

Thermal Properties	Metric	English	Comments
CTE, linear	90.0 μm/m-°C	50.0 μin/in-°F	ISO 11359-2
	@Temperature 23.0 - 55.0 °C	@Temperature 73.4 - 131 °F	
CTE, linear, Transverse to Flow	90.0 μm/m-°C	50.0 μin/in-°F	ISO 11359-2
	@Temperature 23.0 - 55.0 °C	@Temperature 73.4 - 131 °F	
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	ISO 75-1, 2
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	8.00e+15 ohm-cm	8.00e+15 ohm-cm	IEC 60093
Surface Resistance	5.00e+16 ohm	5.00e+16 ohm	IEC 60093
Dielectric Strength	20.0 kV/mm	508 kV/in	IEC 60243-1
Comparative Tracking Index	300 V	300 V	IEC 60112

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China