

## Polyplastics Duranex® 800FP Polybutylene Terephthalate (PBT), Unfilled PBT for film, Extrusion, Super High Viscosity

Category: Polymer, Film, Thermoplastic, Polyester, TP, Polybutylene Terephthalate (PBT), Polybutylene Terephthalate (PBT), Extrusion Grade

## Material Notes:

DURANEX® is a crystalline thermoplastic based on polybutylene terephthalate (PBT) that can be readily strengthened, modified, or otherwise performance enhanced through the addition of glass fibers or other inorganic filler additives. Various grades are available, including flame-retardant, reinforced, and impact-resistant grades. DURANEX®, due to its mechanical strength, heat stability, electrical resistivity and wear and abrasion-resistance, offers great potential as a well-balanced, highly reliable material, having a wide variety of applications including electronic / electro-mechanical and automobile parts and various other functional parts. DURANEX® also assures moldability, dimensional stability, glossy surfaces and various fabrication capabilities providing higher added value.Information provided by PolyPlastics.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Polyplastics-Duranex-800FP-Polybutylene-Terephthalate-PBT-Unfilled-PBT-for-film-Extrusion-Super-High-Viscosity.php

Physical Properties	Metric	English	Comments
Density	1.31 g/cc	0.0473 lb/in <sup>3</sup>	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	53.0 MPa	7690 psi	ISO 527-1,2
Elongation at Break	108 %	108 %	ISO 527-1,2
Flexural Modulus	2.44 GPa	354 ksi	ISO 178
Charpy Impact, Notched	0.490 J/cm <sup>2</sup>	2.33 ft-lb/in <sup>2</sup>	ISO 179/1eA

Thermal Properties	Metric	English	Comments	
Deflection Temperature at 1.8 MPa (264 psi)	56.0 °C	133 °F	ISO 75-1, 2	
Flammability, UL94	HB	НВ		

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China