

## Polyram PlusTek PB300G2 Nylon 6 for Injection Molding, 10% Glass-Fiber Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 10% Glass Fiber Filled

### Material Notes:

10% Glass-fiber reinforced, heat stabilized Nylon 6 for injection molding applications. Information provided by Polyram.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polyram-PlusTek-PB300G2-Nylon-6-for-Injection-Molding-10-Glass-Fiber-Reinforced.php](http://www.lookpolymers.com/polymer_Polyram-PlusTek-PB300G2-Nylon-6-for-Injection-Molding-10-Glass-Fiber-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.28 g/cc	0.0462 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption at Equilibrium	3.0 %	3.0 %	50% RH; ISO 62
Water Absorption at Saturation	9.5 %	9.5 %	ISO 62
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	ISO 2577

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	122	122	
Tensile Strength, Yield	105 MPa	15200 psi	ISO 527
Elongation at Break	4.0 %	4.0 %	ISO 527
Tensile Modulus	4.50 GPa	653 ksi	ISO 527
Flexural Strength	150 MPa	21800 psi	ISO 178
Flexural Modulus	4.60 GPa	667 ksi	ISO 178
Izod Impact, Notched (ISO)	5.00 kJ/m <sup>2</sup>	2.38 ft-lb/in <sup>2</sup>	ISO 180

Thermal Properties	Metric	English	Comments
Melting Point	218 °C	424 °F	ISO 11357
Maximum Service Temperature, Air	110 °C	230 °F	Continuous use
	200 °C	392 °F	Short peaks operation
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	190 °C	374 °F	ISO 75
Flammability, UL94	HB	HB	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Thermal Properties	Metric	English	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	IEC 60093
Dielectric Constant	3.8	3.8	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	80.0 kV/mm	2030 kV/in	IEC 60250

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China