

Polyram RamLloy PBB702 PC/ABS alloy, UV Stabilized

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

UV stabilized PC/ABS alloy for injection molding applications Information provided by Polyram Ram On Ind.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-RamLloy-PBB702-PCABS-alloy-UV-Stabilized.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	DIN 53479
Moisture Absorption at Equilibrium	8.0 %	8.0 %	DIN 53714
Linear Mold Shrinkage	0.0080 cm/cm	0.0080 in/in	
Melt Flow	9.0 g/10 min @Load 5.00 kg, Temperature 240 °C	9.0 g/10 min @Load 11.0 lb, Temperature 464 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	50.0 MPa	7250 psi	ASTM-D638
Elongation at Break	40 %	40 %	ASTM-D638
Tensile Modulus	1.80 GPa	261 ksi	ASTM-D790
Flexural Strength	80.0 MPa	11600 psi	ASTM-D790
Flexural Modulus	2.10 GPa	305 ksi	ASTM-D790
Izod Impact, Notched	5.00 J/cm @Temperature 23.0 °C	9.37 ft-lb/in @Temperature 73.4 °F	ASTM-D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	120 °C	248 °F	DIN 53461
Deflection Temperature at 1.8 MPa (264 psi)	100 °C	212 °F	DIN 53461
Vicat Softening Point	120 °C	248 °F	ASTM-D1525
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	DIN 53482

Electrical Properties

Metric ^{mm}

English ⁱⁿ

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China