

Polyram RamTough PZ126 Polycarbonate, Low Viscosity

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Molded

Material Notes:

General purpose, low viscosity polycarbonate for injection molding applications. Information provided by Polyram.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-RamTough-PZ126-Polycarbonate-Low-Viscosity.php

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in ³	ISO 1183
Water Absorption at Saturation	0.30 %	0.30 %	ISO 62
Linear Mold Shrinkage	0.0050 - 0.0080 cm/cm	0.0050 - 0.0080 in/in	ISO 2577
Melt Flow	20 g/10 min @Load 1.20 kg, Temperature 300 °C	20 g/10 min @Load 2.65 lb, Temperature 572 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	60.0 MPa	8700 psi	ISO 527
Elongation at Break	85 %	85 %	ISO 527
Tensile Modulus	2.35 GPa	341 ksi	ISO 527
Flexural Strength	100 MPa	14500 psi	ISO 178
Flexural Modulus	2.30 GPa	334 ksi	ISO 178
Izod Impact, Notched (ISO)	60.0 kJ/m ²	28.6 ft-lb/in ²	ISO 180

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	132 °C	270 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	120 °C	248 °F	ISO 75
Flammability, UL94	V-2 @Thickness 3.00 mm	V-2 @Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	IEC 60093
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	IEC 60093

Electrical Properties

Metric mm

English in

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China