

Precision Polymer Engineering Perlast® G67P Translucent Perfluoroelastomer

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

A translucent beige compound with semi-crystalline perfluoropolymer nano-filler, specially developed to meet the demands of the semiconductor and bio-analytical industries. Compatible with fluorine based chemistries and universally suitable for both wet and dry semiconductor processes including Lithography, Plasma, PVD, CVD, Etch, Stripping and Cleaning. Perlast® G67P combines a fully fluorinated polymer backbone, a fully fluorinated nano-filler system (no inorganic fillers) and a highly fluorinated cross-linking process, which results in a perfluoroelastomer with unrivalled purity and chemical resistance. Perlast® G67P has a significantly lower compressive modulus than traditional perfluoroelastomers, making it highly compliant. So for a given compression, it exhibits a low reaction force, this results in lower stress on the seal, which leads to longer life expectancy. Applications: Dynamic seals: gate valves; door seals; pendulum valves; ISO valves; bonded gates and lip seals. Static seals: O-rings; body seals; chamber lid seals; cathode assembly seals; electro-static-chuck seals; flange fittings. Wafer-handling products: end effector pads; vacuum suction pads. Wet and dry semiconductor processes: lithography; plasma; PVD; CVD; etch; stripping; cleaning. Laser/optical equipment.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-Perlast-G67P-Translucent-Perfluoroelastomer.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	63	63	ASTM D2240
	60 - 70	60 - 70	°IRHD; ASTM D1415
Tensile Strength, Yield	18.3 MPa	2650 psi	ASTM D412
Elongation at Break	331 %	331 %	ASTM D412
100% Modulus	0.00345 GPa	0.500 ksi	ASTM D412
Compression Set	34.5 %	34.5 %	24 hours @ 200°C; ASTM D395
	41 %	41 %	70 hours @ 204°C; ASTM D395

Thermal Properties	Metric	English	Comments
CTE, linear	520 µm/m-°C	289 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Maximum Service Temperature, Air	275 °C	527 °F	
Minimum Service Temperature, Air	-15.0 °C	5.00 °F	

Descriptive Properties	Value	Comments
Color	translucent beige	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China