

## Precision Polymer Engineering V70H Fluoroelastomer Compound

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Fluoroelastomer Rubber, 66-75 °IRHD. Copolymer of vinylidene fluoride and hexafluoropropylene. Formulated using only those ingredients determined by the United States Federal Food and Drug Administration (FDA). Water and n-Hexane extraction tested in accordance with Code of Federal Regulations Title 21 (CFR21), Section 177.2600. ASTM designation = FKM. ISO designation = FPM. . Also complies to the requirements of USP 25, NF20, 2002, Class 6. Applications: Excellent oil and heat resistance. For repeated use in equipment associated with the production of foodstuffs intended for human consumption. For use with aqueous or fatty foods.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Precision-Polymer-Engineering-V70H-Fluoroelastomer-Compound.php](http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-V70H-Fluoroelastomer-Compound.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	74	74	°IRHD; ASTM D1415
	59 - 89	59 - 89	°IRHD, ±15 change after 72 hours @ 250°C; ASTM D1415
Tensile Strength, Yield	12.0 MPa	1740 psi	ASTM D412
	8.40 - 15.6 MPa	1220 - 2260 psi	±30% change after 72 hours @ 250°C; ASTM D412
Elongation at Break	100 %	100 %	-50% change after 72 hours @ 250°C; ASTM D412
	200 %	200 %	ASTM D412
Compression Set	20 %	20 %	24 hours @ 200°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 °C	392 °F	
Minimum Service Temperature, Air	-10.0 °C	14.0 °F	
Flash Point	>= 315 °C	>= 599 °F	

Descriptive Properties	Value	Comments
Extraction Test, 21 CFR 177.2600	pass	Distilled Water
	pass	n-Hexane

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China