

## Premix Premi-Glas® 1100V-15 Fiberglass Reinforced Thermoset BMC

Category : Polymer , Thermoset , Filled/Reinforced Thermoset

### Material Notes:

Premi-Glas® 1100V-15 is a fiberglass reinforced thermoset bulk molding compound for electrical and flame retardant applications. Key features and benefits are: Non-Halogen FR technology for regulatory compliance Good dimensional stability, including excellent thermal resistance Recognized by Underwriter's Laboratories, File #E42524 Pigmentable for molded-in color, best appearance with mold texture Designed for compression or injection molding in matched metal die molds. Information provided by Premix.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Premix-Premi-Glas-1100V-15-Fiberglass-Reinforced-Thermoset-BMC.php](http://www.lookpolymers.com/polymer_Premix-Premi-Glas-1100V-15-Fiberglass-Reinforced-Thermoset-BMC.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.70 - 1.85 g/cc	1.70 - 1.85 g/cc	
Linear Mold Shrinkage	0.0015 - 0.0035 cm/cm	0.0015 - 0.0035 in/in	Polymerization Shrinkage

Mechanical Properties	Metric	English	Comments
Tensile Strength	31.0 MPa	4500 psi	ASTM D638
Tensile Modulus	14.0 GPa	2030 ksi	ASTM D638
Flexural Strength	95.0 MPa	13800 psi	ASTM D790
Flexural Modulus	9.70 GPa	1410 ksi	ASTM D790
Poissons Ratio	0.30	0.30	
Shear Modulus	5.40 GPa	783 ksi	Calculated
Izod Impact, Notched	3.70 J/cm	6.93 ft-lb/in	ASTM D256
Izod Impact, Unnotched	4.80 J/cm	8.99 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	35.0 $\mu\text{m}/\text{m}\cdot\text{C}$	19.4 $\mu\text{in}/\text{in}\cdot\text{F}$	Z Direction
CTE, linear, Transverse to Flow	25.0 $\mu\text{m}/\text{m}\cdot\text{C}$	13.9 $\mu\text{in}/\text{in}\cdot\text{F}$	XY Direction
Thermal Conductivity	0.300 W/m-K	2.08 BTU-in/hr-ft <sup>2</sup> -F	
UL RTI, Electrical	130 °C	266 °F	UL 746C
UL RTI, Mechanical with Impact	130 °C	266 °F	UL 746C
UL RTI, Mechanical without Impact	130 °C	266 °F	UL 746C
	V-0	V-0	

Flammability UL 94			
Thermal Properties	Metric @ Thickness 1.50 mm	English @ Thickness 0.0591 in	Comments
<b>Electrical Properties</b>			
	<b>Metric</b>	<b>English</b>	<b>Comments</b>
Dielectric Strength	15.0 kV/mm	381 kV/in	ASTM D149
Arc Resistance	180 sec	180 sec	ASTM D495
<b>Processing Properties</b>			
	<b>Metric</b>	<b>English</b>	<b>Comments</b>
Processing Temperature	150 °C	302 °F	Compression or Injection Molding
Clamp Pressure	3.45 - 6.89 MPa	500 - 1000 psi	Molding Pressure

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China