

Premix Premi-Glas® 1200H-10 Fiberglass Reinforced Thermoset SMC

Category : Polymer , Thermoset , Composite SMC , Filled/Reinforced Thermoset

Material Notes:

Premi-Glas® 1200H-10 is a fiberglass reinforced thermoset sheet molding compound for general purpose and HVAC applications requiring thermal stability and stiffness. Key features and benefits are: Good dimensional stability, including excellent thermal resistance; Pigmentable for molded-in color; best appearance with mold texture; Excellent property retention in cold and hot environments; Suitable for outdoor use in applications involving UV exposure and water immersion in accordance with UL746C (f1), see file E42524; Designed for compression molding in matched metal die molds. Information provided by Premix.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Premix-Premi-Glas-1200H-10-Fiberglass-Reinforced-Thermoset-SMC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.70 - 1.85 g/cc	1.70 - 1.85 g/cc	
Linear Mold Shrinkage	0.0020 - 0.0035 cm/cm	0.0020 - 0.0035 in/in	Polymerization Shrinkage

Mechanical Properties	Metric	English	Comments
Tensile Strength	20.0 MPa	2900 psi	ASTM D638
Tensile Modulus	11.0 GPa	1600 ksi	ASTM D638
Flexural Strength	70.0 MPa	10200 psi	ASTM D790
Flexural Modulus	9.50 GPa	1380 ksi	ASTM D790
Compressive Strength	120 MPa	17400 psi	ASTM D695
Poissons Ratio	0.30	0.30	
Shear Modulus	4.20 GPa	609 ksi	Calculated
Izod Impact, Notched	3.10 J/cm	5.81 ft-lb/in	ASTM D256
Izod Impact, Unnotched	3.65 J/cm	6.84 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	35.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	19.4 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	Z Direction
CTE, linear, Transverse to Flow	25.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	13.9 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	XY Direction
Thermal Conductivity	0.300 W/m-K	2.08 BTU-in/hr-ft ² -°F	
UL RTI, Electrical	130 °C	266 °F	UL 746C
UL RTI, Mechanical with Impact	130 °C	266 °F	UL 746C

UL FT1 Mechanical without Impact	130 °C	265 °F	UL 746C
Thermal Properties	Metric	English	Comments
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	

Electrical Properties	Metric	English	Comments
Dielectric Strength	15.0 kV/mm	381 kV/in	ASTM D149
Arc Resistance	180 sec	180 sec	ASTM D495

Processing Properties	Metric	English	Comments
Processing Temperature	150 °C	302 °F	Compression Molding
Clamp Pressure	3.45 - 6.89 MPa	500 - 1000 psi	Molding Pressure

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China