

Premix Premi-Glas® 3140-22 Fiberglass Reinforced Thermoset Thick Molding Compound

Category : Polymer , Thermoset , Filled/Reinforced Thermoset

Material Notes:

Premi-Glas® 3140-22 is a fiberglass reinforced thermoset thick molding compound for electrical and flame retardant applications. Key features and benefits are: TMC compounding process preserves glass integrity for strength vs. BMC. Good dimensional stability, including excellent thermal resistance. Pigmentable for molded-in color; best appearance with mold texture. Recognized by Underwriter's Laboratories, File #E42524. Designed for injection or compression molding in matched metal die molds. Information provided by Premix.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Premix-Premi-Glas-3140-22-Fiberglass-Reinforced-Thermoset-Thick-Molding-Compound.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.75 - 1.85 g/cc	1.75 - 1.85 g/cc	
Linear Mold Shrinkage	0.0015 - 0.0025 cm/cm	0.0015 - 0.0025 in/in	Polymerization Shrinkage

Mechanical Properties	Metric	English	Comments
Tensile Strength	56.0 MPa	8120 psi	ASTM D638
Tensile Modulus	10.0 GPa	1450 ksi	ASTM D638
Flexural Strength	135 MPa	19600 psi	ASTM D790
Flexural Modulus	9.00 GPa	1310 ksi	ASTM D790
Poissons Ratio	0.30	0.30	
Shear Modulus	3.80 GPa	551 ksi	Calculated
Izod Impact, Notched	7.00 J/cm	13.1 ft-lb/in	ASTM D256
Izod Impact, Unnotched	9.00 J/cm	16.9 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	35.0 $\mu\text{m}/\text{m}\cdot\text{C}$	19.4 $\mu\text{in}/\text{in}\cdot\text{F}$	Z Direction
CTE, linear, Transverse to Flow	25.0 $\mu\text{m}/\text{m}\cdot\text{C}$	13.9 $\mu\text{in}/\text{in}\cdot\text{F}$	XY Direction
Thermal Conductivity	0.300 W/m-K	2.08 BTU-in/hr-ft ² -F	
UL RTI, Electrical	130 °C	266 °F	UL 746C
UL RTI, Mechanical with Impact	130 °C	266 °F	UL 746C
UL RTI, Mechanical without Impact	130 °C	266 °F	UL 746C

Thermal Properties Flammability, UL 94	V-0 Metric	V-0 English	Comments
	@Thickness 1.50 mm	@Thickness 0.0591 in	

Electrical Properties	Metric	English	Comments
Dielectric Strength	15.0 kV/mm	381 kV/in	ASTM D149
Arc Resistance	>= 180 sec	>= 180 sec	ASTM D495
Comparative Tracking Index	600 V	600 V	ASTM D2303

Processing Properties	Metric	English	Comments
Processing Temperature	150 °C	302 °F	Injection or Compression Molding
Clamp Pressure	3.45 - 6.89 MPa	500 - 1000 psi	Molding Pressure

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China