

## Proto3000 Objet Digital Materials™ DM\_8210 Rigid Opaque Prototyping Polymer

Category : Polymer , Rapid Prototyping Polymer

### Material Notes:

Primary material: VeroBlueSecondary material: VeroBlackDigital Materials are made up of two Objet materials. The two materials are combined in specific concentrations and structures, to provide the desired mechanical properties and to resemble the product's target materials. Information provided by Proto3000 for their prototyping engineering services.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Proto3000-Objet-Digital-Materials-DM8210-Rigid-Opaque-Prototyping-Polymer.php](http://www.lookpolymers.com/polymer_Proto3000-Objet-Digital-Materials-DM8210-Rigid-Opaque-Prototyping-Polymer.php)

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	50.0 - 60.0 MPa	7250 - 8700 psi	ASTM D638-03
Elongation at Break	15 - 25 %	15 - 25 %	ASTM D638-05
Modulus of Elasticity	2.00 - 3.00 GPa	290 - 435 ksi	ASTM D638-04
Flexural Strength	60.0 - 70.0 MPa	8700 - 10200 psi	ASTM D790-03
Flexural Modulus	1.90 - 2.50 GPa	276 - 363 ksi	ASTM D790-04
Izod Impact, Notched	0.200 - 0.300 J/cm	0.375 - 0.562 ft-lb/in	ASTM D256-06

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	45.0 - 50.0 °C	113 - 122 °F	ASTM D648-06

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China