

## Pyrotek LUMIFELT AL20 High Temperature Kevlar® Felt

Category : Polymer , Thermoset , Aramid

**Material Notes:**

Lumifelt is composed of heat resistant para linked type Kevlar® fiber. Lumifelt is an ideal insulating pad for a variety of applications. It is needle punched to give it high tensile strength and good holding strength to maintain product integrity. Applications Insulating pads for high-temperature glass transfer applications Sealing materials for annealing furnace of nonferrous metal Heat shields for furnace doors Cushioning material for hot glass transfer and conveyance Insulating pads for conveyor line and shock absorber Covering material for conveyor rolls Advantages Asbestos-free Excellent heat and abrasion resistance High elasticity Long life to cyclic loading Good recovery from compression Light weight Good coefficient of friction Will not damage nor blur the surface of glass containers or other high-temperature glass products Porosity reduces the temperature difference between pad contacting and non-contacting surfaces Information provided by Pyrotek.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Pyrotek-LUMIFELT-AL20-High-Temperature-Kevlar-Felt.php](http://www.lookpolymers.com/polymer_Pyrotek-LUMIFELT-AL20-High-Temperature-Kevlar-Felt.php)

Physical Properties	Metric	English	Comments
Density	0.400 g/cc	0.0145 lb/in <sup>3</sup>	
Permeability	1.1 @Thickness 10.0 mm	1.1 @Thickness 0.394 in	cc/sec/cm <sup>2</sup> , Air

Mechanical Properties	Metric	English	Comments
Compressive Strength	0.9807 MPa	142.2 psi	to 25% compression
Coefficient of Friction, Static	0.24	0.24	
Abrasion	0.83	0.83	Thickness reduction after 10,000 abrasion cycles under 500 g/cm <sup>2</sup> load at 400°C
	0.90	0.90	Thickness reduction after 10,000 abrasion cycles under 500 g/cm <sup>2</sup> load at 320°C

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.150 W/m-K	1.04 BTU-in/hr-ft <sup>2</sup> -°F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China