

Quadrant EPP Ketron® HPV PEEK High Pressure Velocity Polyetherether Ketone (ASTM Product Data Sheet)

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK)

Material Notes:

This bearing grade of extruded Ketron PEEK offers the lowest coefficient of friction and best machinability of all Ketron grades. It is ideal for low wear, high PV parts that require chemical resistance. Data provided by Quadrant Engineering Plastic Products. Excellent chemical resistance Very low moisture absorption Inherently good wear and abrasion resistance Unaffected by continuous exposure to hot water or steam

Order this product through the following link:

http://www.lookpolymers.com/polymer_Quadrant-EPP-Ketron-HPV-PEEK-High-Pressure-Velocity-Polyetherether-Ketone-ASTM-Product-Data-Sheet.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.44 g/cc	1.44 g/cc	ASTM D792
	@Temperature 22.8 °C	@Temperature 73.0 °F	
Water Absorption	0.050 %	0.050 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	0.30 %	0.30 %	ASTM D570

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	85	85	ASTM D785
Tensile Strength	75.8 MPa	11000 psi	ASTM D638
	@Temperature 22.8 °C	@Temperature 73.0 °F	
Elongation at Break	2.0 %	2.0 %	ASTM D638
Tensile Modulus	5.86 GPa	850 ksi	ASTM D638
	@Temperature 22.8 °C	@Temperature 73.0 °F	
Flexural Strength	190 MPa	27500 psi	ASTM D790
	@Temperature 22.8 °C	@Temperature 73.0 °F	
Flexural Modulus	7.58 GPa	1100 ksi	ASTM D790
	@Temperature 22.8 °C	@Temperature 73.0 °F	
Compressive Strength	138 MPa	20000 psi	ASTM D732
	@Strain 10.0 %, Temperature 22.8 °C	@Strain 10.0 %, Temperature 73.0 °F	
Compressive Modulus	3.45 GPa	500 ksi	ASTM D695
	@Temperature 22.8 °C	@Temperature 73.0 °F	

Mechanical Properties	Metric	English	Comments
Shear Strength	68.9 MPa	10000 psi	ASTM D790
	@Temperature 22.8 °C	@Temperature 73.0 °F	
Izod Impact, Notched	0.374 J/cm	0.700 ft-lb/in	ASTM D256 Type A
Coefficient of Friction, Dynamic	0.21	0.21	Dry vs. Steel; QTM 55007
K (wear) Factor	201 x 10 ⁻⁸ mm ³ /N-M	100 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	QTM 55010
Limiting Pressure Velocity	0.701 MPa-m/sec	20000 psi-ft/min	4:1 safety factor; QTM 55007

Thermal Properties	Metric	English	Comments
CTE, linear	30.6 µm/m-°C	17.0 µin/in-°F	ASTM E831
	@Temperature -40.0 - 149 °C	@Temperature -40.0 - 300 °F	
Thermal Conductivity	0.245 W/m-K	1.70 BTU-in/hr-ft ² -°F	ASTM F433
Melting Point	340 °C	644 °F	Crystalline, Peak; ASTM D3418
Maximum Service Temperature, Air	250 °C	482 °F	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	195 °C	383 °F	ASTM D648
Flammability, UL94	V-0	V-0	1/8 inch (Estimated Rating)

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	<= 10000 ohm	<= 10000 ohm	EOS/ESD S11.11

Compliance Properties	Metric	English	Comments
3A-Dairy	No	No	
Canada AG	No	No	
FDA	No	No	
NSF	No	No	
USDA	No	No	
USP Class VI	No	No	

Chemical Resistance Properties	Metric	English	Comments
Acids, Strong (pH 1-3)	Limited	Limited	
Acids, Weak	Acceptable	Acceptable	

Chemical Resistance Properties	Metric	English	Comments
Alkalies, Strong (pH 11-14)	Acceptable	Acceptable	
Alkalies, Weak	Acceptable	Acceptable	
Chlorinated Solvents	Acceptable	Acceptable	
Conductive / Static Dissipative	Yes	Yes	
Continuous Sunlight	Acceptable	Acceptable	
Hot Water / Steam	Acceptable	Acceptable	
Hydrocarbons - Aliphatic	Acceptable	Acceptable	
Hydrocarbons - Aromatic	Acceptable	Acceptable	
Inorganic Salt Solutions	Acceptable	Acceptable	
Ketones, Esters	Acceptable	Acceptable	

Descriptive Properties	Value	Comments
Color	Natural	
Machinability	7	1-10, 1=Easier to Machine

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China